

## Specification Sheet

## **Sponge Rubber Closed Cell R-338-V**

Physical Property	Test Method	Result
Туре		R-338-V
Polymer		PVC / NBR
Color		Natural
ASTM D-1056		2B1/2B2
ASTM D-6576-67 Classification		SBE41/SBE42
SAEJ18 APR2002		2B1/2B2
Density (lbs/ft <sup>3</sup> )	ASTM D 1056	5 - 7.5
25% Compression Resistance (%)	ASTM D 1056	3.5 - 7
50% Compression Set (%)	ASTM D 1056	35
Tensile Strength	ASTM D 412 (DIE A)	80 psi
Elongation (%)	ASTM D 412 (DIE A)	200
Water Absorption (lbs/ft²)	ASTM D 1667	0.1
Flammability	FMVSS302	Pass

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.