



HANNA RUBBER COMPANY

# Specification Sheet

## Sponge Rubber Closed Cell R-493-T

Physical Property	Test Method	Result
Type		R-493-T
Polymer		EPDM
Color		Black
ASTM D-1056		2A3
ASTM D-6576-67 Classification		RE42 / RE43
SAEJ18 APR2002		2A3
Density (lbs/ft <sup>3</sup> )	ASTM D 1056	18 - 28
25% Compression Resistance (%)	ASTM D 1056	9 - 13
50% Compression Set (%)	ASTM D 1056	25
Tensile Strength	ASTM D 412 (DIE A)	110 psi
Elongation (%)	ASTM D 412 (DIE A)	150
Low Temperature Flexibility	ASTM D 1056	-65 °F
Water Absorption (lbs/ft <sup>2</sup> )	ASTM D 1667	0.01
Flammability	FMVSS302	Pass

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.