



HANNA RUBBER COMPANY

Specification Sheet

NA1000M

Service Limits

Type	Description	Value
Temperature Limits	Maximum	720°F (380°C)
	Continuous Max	390°F (200°C)
Pressure Limits	Maximum	1450 psi (70 bar)
	Continuous Max	580 psi (50 bar)
ASTM F104	Line Call Out	713230E23M6
Color	Black	
Available Sheet Sizes	Thickness	1/64", 1/32", 1/16", 3/32", 1/8"
	Sheet Sizes	59" x 63"
		59" x 126"

Typical Physical Properties

ASTM Test Method	Property	Value
-	Density	118 lb/ft ³ (1.9 gm/cc)
F36	Compressibility	10-20%
F36	Recovery	min 40%
F38	Tensile Strength Across Grain	2680 psi (18.5 N/mm ²)
F495	Ignition Loss	Max 37%
F146	Thickness Increase After 5 Hour Immersion	
-	ASTM IRM 903 @ 300°F (150°C)	Max 20%
-	ASTM Fuel B @ 77°F (25°C)	Max 15%
F136	Weight Increase After 5 Hour Immersion	
-	ASTM IRM 903 @ 300°F (150°C)	Max 20%
-	ASTM Fuel B @ 77°F (25°C)	Max 15%

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.